
FineTOUGHNitrile Gloves




PR	PRODUCT INFORMATION		
MATERIAL	Nitrile		
COLOR	Indigo or white		
TYPE	Ambidextrous, non-sterile, single-use		
INTERIOR	Powder-free		
EXTERIOR	Textured fingertips		
COUNTRY OF ORIGIN	Malaysia		
STORAGE	Store in original packaging in a cool, dry and well ventilated area, away from dust, direct sunlight, moisture, x-ray and excessive heat above 100°F (37°C)		

PHYSIC	PHYSICAL PROPERTIES			
AQL	1.5			
GLOVE WEIGHT	3g (medium)			
GLOVE THICKNESS	2.6mil			
GLOVE LENGTH	9"/240mm			
PALM WIDTH SIZING Measure widest part of the knuckles	S (85mm +/-5), M (95mm +/-5), L (106mm +/-5), XL (116mm +/-5)			
	BEFORE AGING	AFTER AGING		
TENSILE STRENGTH (MPA)	min. 14	min. 14		
ULTIMATE ELONGATION	min. 500%	min. 400%		



QUALITY STANDARDS				
FDA STATUS	(21 CFR 177) compliant for food handling 510(k) cleared for medical use			
AUDIT STANDARDS	Manufactured in an ISO 9001:2015 and an ISO 13485:2016 facility Halal and HACCP certified (Indigo only) Manufactured in a Certified WRAP Facility			
TEST STANDARDS	EN 16523-1 Resistance to Chemical Permeation EN ISO 374-5:2016 Resistance to Bacteria, Fungi & Virus EN ISO 374-1:2016+A1:2018/Type B ASTM D6319 & EN 455 ASTM F1671 Viral Penetration ASTM D6978 Chemotheraphy Drug Tested			





	PACKAGING & ORDERING INFORMATION					
WHITE CODE	INDIGO CODE	SIZE	PURCHASE UNIT	CARTON DIMENSIONS (LxWxH)	CARTON WEIGHT	CUBIC METRE
1172202	1162202	S				
1172302	1162302	М	1 carton of 2,000 Gloves	76 V 25 V 24 Fam	6.0014	0.02m3
1172402	1162402	L	(200/box x 10)	36 X 25 X 24.5cm	6.89kg	0.02m ³
1172502	1162502	XL				

MANDATORY STATEMENTS EN ISO 374-1:2016

"This information does not reflect the actual duration of protection in the workplace and the differentiation between mixtures and pure chemicals."

"The chemical resistance has been assessed under laboratory conditions from samples taken from the palm only (except in cases where the glove is equal to or over 400mm - where the cuff is tested also) and relates only to the chemical tested. It can be different if the chemical is used in a mixture."

"It is recommended to check that the gloves are suitable for the intended used because the conditions at the workplace may differ from the type depending on temperature, abrasion and degradation."

"When used, protective gloves may provide less resistance to the dangerous chemical due to changes in physical properties. Movements, snagging, rubbing, degradation caused by the chemical contact etc. may reduce the actual use time significantly. For corrosive chemicals, degradation can be the most important factor to consider in selection of chemical resistant gloves."

"The penetration resistance has been assessed under laboratory conditions and relates to the tested specimen."

RESISTANCE	OF GLOVES	S TO PE	RMEATION	BY CHEMI	CALS		
CHEMICAL			EN ISO 374-1:2 PERFORMA		EN 374-4 MEAN DEGRA		
Chlorhexidine Digluconate 4%*			6		19.0)	
Sodium Hydroxide 40% (K)			6	6		-42.9	
Sodium Hypochlorite 10-13%			6	6 14.7		7	
Sulphuric Acid 50%			6	6 -20.5		5	
Acetic Acid 10%			4		66.	7	
Ethidium Bromide 5%		6		3.4			
Formaldehyde 37% (T)		3	5.0				
ric Acid 65% (M)		0	0 97.6		5		
Glutaraldehyde 50%			6		27.4	1	
Phenol 0.1%	ol 0.1%		6		33.8		
lydrogen Peroxide 30% (P)		2		22.8			
Methanol in Water 1.5%		6		21.9			
sopropanol 70%		0		62.2			
Ethanol 35%		0		38.8			
Acetic Acid 99% (N)		0		93.9			
mmonium Hydroxide 25% (O)		0		-52.0			
Povidone-iodine 3%			6		33.7	7	
Sodium Percarbonate 10%	ercarbonate 10% 6 15.4		ļ				
* The minimum observable permeation rate was 7	µg/cm²/min						
EN ISO 374-1:2016+A1:2018 - permeation levels ar	e based on breakth	rough time	s as follows:				
Performance Level:	1	2	3	4	5	6	
Minimum breakthrough time (Min):	>10	>30	>60	>120	>240	>480	

EN 374-4:2019 - Degradation results indicate the change in puncture resistance of the gloves after exposure to the challenge chemical

Safety gloves to protect against chemicals are classified according to their permeation time (time taken for the chemical to penetrate the glove) and number of chemicals tested:

- Type A at least 30min each for at least 6 test chemicals
- Type B at least 30min each for at least 3 test chemicals
- Type C at least 10min each for at least 1 test chemicals

EN ISO 374-5:2016 - Resistance to Bacteria and Fungi = Pass, Resistance to Virus = Pass

EN 455-2:2009 - Medical gloves for single use = \geq 6.3N (requirement is \geq 6.0)

CHEMOTHERAPY DRUGS PERMEATION TEST (ASTM D6978-05)				
CHEMICAL	MIN BREAKTHROUGH DETECTION TIME (mins)	OBSERVATIONS		
*Carmustine (BCNU) (3.3 mg/mL)	Not Recommended	Moderate swelling & no degradation		
Cisplatin (1.0 mg/mL)	> 240	Slight swelling & no degradation		
Cyclophosphamide (Cytoxan) (20.0 mg/mL)	> 240	Slight swelling & no degradation		
Cytarabine (100 mg/mL)	> 240	Slight swelling & no degradation		
Dacarbazine (DTIC) (10.0 mg/mL)	> 240	Slight swelling & no degradation		
Doxorubicin Hydrochloride (2.0 mg/mL)	> 240	Slight swelling & no degradation		
Etoposide ((20.0 mg/mL)	> 240	Slight swelling & no degradation		
Fluorouracil (50.0 mg/mL)	> 240	Slight swelling & no degradation		
Ifosfamide (50.0 mg/mL)	> 240	Slight swelling & no degradation		
Methotrexate (25.0 mg/mL)	> 240	Slight swelling & no degradation		
Mitomycin C (0.5 mg/mL)	> 240	Slight swelling & no degradation		
Mitoxantrone (2.0 mg/mL)	> 240	Slight swelling & no degradation		
Paclitaxel (Taxol) (6.0 mg/ml)	> 240	Moderate swelling & no degradation		
*Thiotepa (10.0 mg/mL)	Not Recommended	Slight swelling & no degradation		
Vincristine Sulfate (1.0 mg/mL)	> 240	Slight swelling & no degradation		
*Warning: Not recommended for use with Carmustine	and Thiotepa			



Contact us today to receive samples or for more information on this product.



